



INVESTOR IN PEOPLE

BEST AVAILABLE COPY

The Patent Office
 Concept House
 Cardiff Road
 Newport
 South Wales
 NP10 800

18 OCT 2004

WIPO


PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated

5 October 2004


**PRIORITY
 DOCUMENT**

SUBMITTED OR TRANSMITTED IN
 COMPLIANCE WITH RULE 17.1(a) OR (b)



The
Patent
Office

30SEP03 E840763-8 D00019
P01/7700 0-00-0327/80-8



The Patent Office
Cardiff Road
Newport
Gwent NP9 1RH

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

P035519GB

2. Patent application number

(The Patent Office will fill in this part)

0322760.0

29 SEP 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Mars, Incorporated
6885 Elm Street
McLean
VA 22101
USA

Patents ADP number (if you know it)

82700 84001

If the applicant is a corporate body, give the country/state of its incorporation

Delaware, USA

4. Title of the invention

COMPOSTABLE PACKAGING MATERIALS AND METHODS

5. Name of your agent (if you have one)

Carpmaels & Ransford

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

43-45 Bloomsbury Square
London
WC1A 2RA

Patents ADP number (if you know it)

83001 /

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body

Yes

See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description	12
Claim(s)	2
Abstract	1
Drawing(s)	2 + 2

SN

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77) 1

Request for preliminary examination and search (Patents Form 9/77) 1

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

Carpmaels & Ransford

Date

29th September 2003

12. Name and daytime telephone number of person to contact in the United Kingdom

Dr. Anthony James

020-7242 8692

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

COMPOSTABLE PACKAGING MATERIALS AND METHODS

The present invention relates to compostable sheet materials for the manufacture of environmentally friendly packaging. The invention also relates to methods of making packages from such sheet materials, and to packages obtainable thereby.

GB-A-2121762 describes sealed beverage packages containing a product for preparing a beverage in admixture with water, the package comprising a sachet of flexible film material and an integral nozzle for water injection into the package.

10 The beverage escapes from the package through an outlet made by the user cutting open the bottom of the package, or the package may comprise means for enabling a user to open the base of the sachet easily, for example peelable tabs, edge nicks, tear strings or tear strips. However, in each case the intervention of a user is needed to open the bottom of the sachet.

15 EP-A-0179641 describes a related beverage brewing system, in which the package is a sachet of flexible film material with an integral nozzle for water injection. The bottom edge of the beverage sachet is sealed by bonding together two sheets of flexible film material with a pressure-sensitive adhesive. When the interior of the sachet is pressurised by injection of water to brew beverage, the

20 resulting pressure in the sachet separates the pressure-sensitive adhesive, thereby allowing the beverage to flow out of the bottom of the sachet. This beverage brewing system has enjoyed great commercial success. However, the need to apply a pressure sensitive adhesive adds to the complexity of manufacturing these sachets. Furthermore, the sachets described in this

25 reference are not biodegradable or compostable.

Polylactic acid and lactic acid copolymers are thermoplastic and biodegradable and compostable. When the polymers are placed in soil or sea water, the

30 polymers start to decompose. In a compost, these materials biodegrade rapidly. The degradation products of these polymers are lactic acid, carbon dioxide and water, all of which are nontoxic.

Polymers of lactic acid are usually prepared from a cyclic dimer of lactic acid which is called lactide. In a typical copolymerization of lactic acid, lactide and glycolide, (a dimer of glycolic acid) are mixed, and ring-opening polymerization is carried out.

5 In the alternative, the polymers may be prepared directly by condensation of lactic acid or a mixture of lactic acid and glycolic acid, but in these direct condensations a high molecular weight polymer cannot be obtained even if the reaction is carried out for a long time. On the other hand, the ring-opening polymerization of lactide or of a mixture of lactide and glycolide can provide a high molecular weight straight-

10 chain polyester. Suitable polymerisation processes are described in EP-A-0624615 and WO-A-02100921.

Lactic acid polymers and copolymers are thermoplastic, but heat sealing of films of such polymers is difficult because of heat distortion and shrinkage of the films, and

15 because the films tend to stick to the sealing jaws of the heat sealing apparatus.

EP-A-0514137 describes degradable laminates comprising a surface layer of a polylactide polymer or copolymer, wherein the surface layer is laminated to a layer of regenerated cellulose, film, paper, leather or cloth.

20

The present invention provides a compostable sheet material comprising a compostable substrate layer, a first compostable and sealable layer on a first side of the substrate layer, and a second compostable and sealable layer overlying said first heat-sealable layer.

25

The term "compostable" signifies that the material is substantially broken down within a few months, preferably within a few weeks, when it is composted. Typically, the sheet material is at least about 90% composted within six months, as determined by the method of ISO14855, as in EN13432. Typically, all

30 components of the sheet material are compostable, but in some embodiments there may be a non-compostable component, additive or layers as allowed in EN13432.

The Substrate Layers

The substrate layer may be thermoplastic or non-thermoplastic, but in any case it usually has a melting temperature higher than those of the sealant layers in order to provide support to the sealant layers during thermic sealing. Typically, the substrate layer comprises a printing substrate material. Suitable substrate materials include paper and cellophane. Exemplary papers for use in the invention include art paper (coated paper), kraft paper, rolled sheet, rice paper, cross paper and paper-board. The paper may contain regenerated pulp.

10

The substrate layer may itself be a laminate, for example a laminate of a printing substrate layer, optionally an oxygen barrier layer, optionally a protective outer layer, and optionally other layers.

15 Suitable materials for inclusion as an oxygen barrier layer in the substrate include polyvinyl alcohol (PVOH), ethylene vinyl alcohol (EVOH), starch and starch derivatives. Yet other suitable oxygen barrier layers comprise inorganic (e.g. silicon) oxides, inorganic nitrides, or inorganic oxide nitrides. These materials have the benefit of being compostable.

20

The Sealant Layers

A characterizing feature of the present invention is the provision of at least two different compostable sealing layers on the support. This allows the sealing properties of the sheet material to be controlled to a higher degree than before, and in particular allows two or more sealing strengths to be achieved with a single sheet. For example, the material of the second heat-sealable layer may have a lower sealing initiation energy than the material of the first heat-sealable layer. In such embodiments, it is possible to bond the sheet with a light sealing strength, such that just sufficient energy is used to bond the second sealable layers only. It is also possible to bond with a high sealing strength by applying sufficient energy and/or pressure to bond both sealant layers together. In any case, the chemical

30

and/or stereochemical composition of the first and second sealing layers are different so as to provide different sealing properties to the two layers.

A further advantage of multiple sealing layers is that the seal strengths may be independently controlled by selection of the polymer composition and processing. It may be seen by one skilled in the art that such multiple layers may be achieved by co-extrusion of a single film, or by lamination of individual layers.

It will be appreciated that references to sealable layers in general usually refers to heat-sealable layers, i.e. thermoplastic layers. However, the present invention contemplates not only thermic (heat) sealing but also sealing by ultrasonic energy, induction or other suitable means, with or without the application of pressure.

Thermoplastic compostable polymers that could be used for the sealable layers include polymers and copolymers of lactic acid, polyhydroxybutyrates, polyvinyl alcohols (PVOH), ethylene vinyl alcohols (EVOH), and mixtures thereof.

Suitably, at least one of the first and second sealable layers comprises, or consists essentially of, polylactic acid or a copolymer of lactic acid and a hydroxycarboxylic acid. Such polymers can be strongly adhered to a substrate such as paper, by adhering or applying the polymer to the substrate in the form of a film or a solution. The resulting laminates are excellent in moisture-proofness, and have high mechanical strength. In certain embodiments, both of the first and second sealable layers comprise, or consists essentially of, polylactic acid or a copolymer of lactic acid and hydroxycarboxylic acid. In such embodiments, the different sealing properties of the first and second sealable layers are achieved by using polymers of different molecular structures and/or by the use of different plasticisers in the different layers, and/or by using different proportions of stereoisomers of one of the monomers to form the polymer. For example, varying the D/L ratio of the lactic acid used to form polylactic polymers and copolymers has a significant effect on sealing properties of the polymers. The raw materials of the polymer are lactic acid, lactide which is a cyclic dimer of lactic acid, and other hydroxycarboxylic acids. Other hydroxycarboxylic acids include, for example, glycolic acid, 3-

hydroxybutyric acid, 4-hydroxybutyric acid, 4-hydroxyvaleric acid, 5-hydroxyvaleric acid and 6-hydroxycaproic acid.

These polymers can be directly prepared through dehydrating polycondensation from lactic acid or other hydroxycarboxylic acid or through ring-opening polymerization from lactide, glycolide, epsilon -caprolactone or a mixture of these compounds. A copolymer prepared by transesterification of polylactic acid with other hydroxycarboxylic acid polymers can also be used. The monomers may be present in any stereoisomeric form, and/or as a mixture of different stereoisomers, and the sealing properties of the polymers will be influenced by the stereochemical composition. For example, the lactic acid unit which constituted these polymers can be L-lactic acid, D-lactic acid or a mixture of these lactic acids. Poly-L-lactic acid (PLLA) is more crystalline and has a higher heat sealing temperature than polymers of mixed D/L lactic acids.

The preferred polymers for use in the sealing layers of the sheet materials of the present invention suitably have an average molecular weight of from 10,000 to 1,000,000, and a polymerization degree of from 150 to 20,000. In some embodiments, the molecular weight of the polymer in the first heat sealing layer is higher than that of the polymer in the second heat sealing layer.

Plasticizers can be added in order to provide flexibility or to adjust the heat sealing properties of the polylactide layers. Plasticizers which can be used include, for example, diethyl phthalate, dioctyl phthalate, dicyclohexyl phthalate and other phthalic acid esters; di-isobutyl adipate, di-n-octyl adipate, di-n-butyl sebacate, di-2-ethylhexyl sebacate, di-2-ethylhexyl azelate and other aliphatic dicarboxylic acid esters; diphenyl 2-ethylhexyl phosphate, diphenyl octyl phosphate and other phosphoric acid esters; tributyl acetylcitrate, tri-2-ethylhexyl acetylcitrate, tributyl citrate and other hydroxypolycarboxylic acid esters; methyl acetylricinoleate, amyl stearate and other aliphatic carboxylic acid esters; glycerol triacetate, triethylene glycol dicaprylate and other polyhydric alcohol esters; epoxylated soybean oil, octyl epoxystearate and other epoxy-base plasticizers; and polypropylene glycol adipate, polypropylene glycol sebacate and other polyester base plasticizers. In

food packaging applications, the plasticiser should be one of those approved for use in food packaging.

The amount of the plasticizer for use is usually from 5 to 50% by weight, preferably from 5 to 20% by weight for the polymer composition. The plasticizer may be added to the polymer as a solution in a solvent, or in molten state.


The thickness of the sealant layers may vary in accordance with this invention. In one embodiment of this invention, for example, the thickness of each of the first and second sealant layers is independently from about 1 to about 40 micrometers, preferably from about 2 to about 20 micrometers. The total basis weight of the sealing layers may for example be from about 10 to about 100g/m², suitably from about 20 to about 50g/m². The total thickness of the multilayer sealant film is typically from about 10 to about 100 micrometers, for example from about 20 to about 60 micrometers.

A suitable method of manufacture of a multilayer sealant film is by using a blown film coextrusion process, although other methods of manufacture of the film may be used. The multilayer sealant film may then be laminated to the substrate sheet.

20

Lamination can be carried out by various method such as thermic bonding, solution coating, hot-melt coating, extrusion lamination, and adhesive lamination. Suitable adhesives include compostable adhesives such as polylactides, gelatin, casein and starch. The surface of the substrate can also be precoated prior to lamination, for example with an oxygen barrier layer or with an organic titanium compound, organic silane compound or polyethyleneimine. In some cases, the substrate paper can be previously impregnated with lactic acid, other hydroxycarboxylic acid, lactide, glycolide or epsilon -caprolactone.

30 In a second aspect, the present invention provides an environmentally friendly package comprising a compostable sheet material according to the present invention.



In the package, normally at least one region of the sheet material is bonded to a second region of the package. In certain embodiments a first region of the sheet material is sealed to a second region of sheet material according to the present invention. The second region may be on the same sheet folded over, or it may be on a separate sheet of the material, but in any case the bonding will normally be thermic bonding of the respective sealing layers in face-to-face relationship, or it may be bonding by ultrasound or induction, with or without the application of pressure.

10 As already discussed, it is a particular advantage of the sheet materials according to the present invention that the multiple sealing layer permits the sealing strength to be controlled, depending on whether sealing is made through just the second sealing layer, or whether it is made through both sealing layers. Accordingly, in the package according to the present invention, the sheet material may have both a first region of sealing having a relatively high heat sealing strength, and a second region of sealing having a relatively low heat sealing strength. The low sealing strength region may be convenient to assist opening of the package by breaking only the weaker seal.

20 In certain embodiments, the package may contain a foodstuff, such as a shelf-stable ready to eat foodstuff, for example a full moisture foodstuff. Examples include shelf-stable soups, sauces, and/or full moisture starchy foodstuffs such as rice or pasta. In these embodiments the region of relatively weak bonding can be used to provide a pressure release feature, whereby the weakly bonded region breaks open when the internal pressure in the package exceeds a predetermined threshold. This feature permits reheating of the products in a microwave oven with controlled pressure relief.

30 It is envisaged that the sheet materials according to the present invention will also be especially useful for making individual, disposable, compostable capsules or sachets for beverage making ingredients to be used in beverage dispensing installations. Accordingly, the package according to the second aspect of the present invention may be a beverage making capsule that contains a beverage

making ingredient. Suitable ingredients include tea (leaf or instant), coffee (ground or instant), drinking chocolate (powder or concentrate), beverage whitener (solid or liquid), or a soft drink concentrate such as a water soluble or water dispersible syrup or sweetened powder concentrate.

5

In certain embodiments, the beverage making ingredient is an infusible beverage brewing ingredient, such as leaf tea or ground coffee. In such embodiments the capsule may further comprise a compostable filter sheet inside the capsule and bonded to an internal surface of the capsule. Typically, the amount of ingredient in the package is sufficient for the preparation of one portion of beverage, i.e. from about 25 to about 500 ml, preferably from about 100ml to about 250ml. For example, the package may contain from about 2 g to about 12 g of ground coffee or from about 1 g to about 9 g of leaf tea.

15 It will be appreciated that the moisture and frequently heat introduced into the capsule during preparation of a beverage from the capsule will themselves initiate and accelerate the breakdown of the degradable materials making up the capsule. Typically the beverage making capsule according to this aspect of the invention is at least about 90% composted within 100 days after brewing a beverage from the capsule, as determined by composting in accordance with EN13432.

20

In certain embodiments, the package according to the present consists essentially of oxygen-impermeable compostable film material, optionally a compostable filter material inside the capsule body, and optionally a compostable injection nozzle.

25

The package comprises at least one compostable sheet. In certain embodiments, the package comprises two compostable sheets bonded in face to face relationship to provide a flexible sachet. In other embodiments, a sachet is formed by folding-over a single compostable sheet, and bonding the edges of the sheet together to form the edges of the sachet.

30

In certain embodiments, the package further comprises a nozzle for water injection to pressurize the package. The nozzle may be inserted into a top edge of the

sachet. Suitable sachet constructions are as described in EP-A-0179641 or GB-A-2121762, the entire contents of which are incorporated herein by reference. In other embodiments, there is no nozzle, for example if the package is to be internally pressurized by heating, or if the package is to be internally pressurized by injection of water into the package through a hollow injector tube that pierces a side of the package. The nozzle may be made of a compostable polymer, for example a polylactide, which welds entirely to the sealable layer of the sheets, forming leak-free seals.

10 In certain embodiments a flexible reinforcing strip may be attached to the compostable sheet proximate to the weakly bonded seal to increase the stiffness of the sheet in that region and thereby provide more controlled opening of the package. Suitable reinforcing strips are described in WO99/05036, the entire content of which is incorporated herein by reference.

15

As discussed above, the bonding between the first and second sheets may be weaker in a first region of the margin than in the remainder of the margin, whereby the capsule body can open by separation of the first and second sheets in the first region when the interior of the capsule body is pressurized.

20

In a third aspect, the present invention provides a method of manufacture of an environmentally friendly package comprising the step of providing a compostable sheet material according to the present invention, and sealing an area of said sheet material to form said package. Preferably, the method is adapted for the production of a package according to the second aspect of the invention.

25

The sealing is normally thermic sealing, but it may for example alternatively or additionally comprise ultrasonic, induction and/or pressure bonding. As already discussed, the step of sealing may be carried out under a first set of conditions in a first region of said area and under a second set of conditions different from said first set of conditions in a second region of said area, whereby the peel strength (sealing strength) of the resulting seal is different in said first and second regions.

30

Certain embodiments of the method of the invention comprise the steps of: placing two webs of the compostable sheet material in face-to-face relation; and bonding the webs together around a margin to form a capsule body. In these embodiments, the method may further include bonding the webs to a water
5 injection nozzle as described above. The nozzle may be made of a compostable polymer, for example a polylactide, which welds entirely to the sealable layer of the sheets, forming leak-free seals.

Certain embodiments of the present invention will now be described further, by
10 way of example, with reference to the accompanying drawings, in which:

Figure 1 shows a plan view of a first sealed package according to the present invention;

Figure 2 shows a sectional view along A-A of the inventive package of Figure 1; and

15 Figure 3 shows a graph of sealing strength against sealing temperature for a sheet material according to the present invention.

Referring to Figures 1 and 2, the package according to the invention is generally similar to the sachet described in EP-A-0179641. It comprises two compostable
20 laminate sheets 1,2. Each laminate sheet comprises an outer layer of paper (Kraft 40g/m²) an inner multilayer sealing film. The sealing film is a PLA laminate available from Hoechst Trespaphan GmbH under the Registered Trade Mark BIOPHAN PLA 121 and has total thickness 30 micrometers. The sealing film comprises a core of relatively high-melting-point, relatively crystalline PLLA and a
25 surface layer of relatively lower melting point, relatively amorphous PLA containing a higher proportion of the D-lactate stereoisomer. The sealing film is laminated to the paper by means of a compostable adhesive, such as a polylactate adhesive.

The front and back sheets 1,2 are bonded together along edge seams 4. A nozzle
30 5 is inserted into the top seam of the sachet. A flange 11 on the nozzle enables the sachet to be gripped by a clamp.

Within the sachet there is a W-shaped sheet 8 of compostable filter material of polylactide spun-bonded fibers that is thermally bonded to the front and back faces of the sachet on each side over an area 10 as shown. The filter 8 is provided with a centre fold 9 whose apex points upwardly as shown in Figure 2. The filter 8 supports a quantity of ground coffee 12. In use, the filter 8 is everted as described in more detail in EP-A-0179641.

The edge seams 4 and top seam of the sachet are bonded together with high sealing strength using temperatures in excess of the crystalline melting point of the PLLA film (i.e. $>160^{\circ}\text{C}$). The bottom seam 13 of the sachet is bonded with a relatively low sealing strength using temperatures of about 100°C to about 150°C , i.e. above the softening point of the amorphous sealing layer, but below the crystalline melting point. Nevertheless, the sachet provides an oxygen and moisture-impermeable enclosure for the coffee until the sachet is used.

15

In use, the sachets are inserted into a suitable beverage brewing machine, where they are gripped by a clamp (not shown) under the nozzle flange. A hollow needle is inserted into the nozzle, and hot water is injected at a pressure of approximately 0.5 bar gauge to brew coffee inside the sachets. The pressure of the hot water causes the weakly bonded margin 13 at the bottom of the sachets to peel apart, releasing the resulting coffee in a controlled fashion.

20

Test Methods

The heat seal strength of the sheet materials was measured using a test method which measures the force required to separate a seal after the material has cooled to 23°C . temperature. The film samples were exposed to a relative humidity of 50 percent and a temperature of 23°C . for a minimum of 24 hours prior to testing.

Heat sealing was carried out according to the following conditions:

Specimen Width: 25 mm

Sealing Time: 2 seconds

Sealing Pressure: 3 bar

30

Temperature Range: 70 °C -190 °C.

- 5 The seal strength of the film samples was determined using an Instron Tensile Tester. The results are shown in Fig.1. It can be seen that a first sealing strength plateau is reached in the sealing temperature range about 90°C to about 150°C, and a second, higher sealing strength is achieved in the sealing temperature range about 170°C to about 190°C.
- 10 The above embodiments have been described by way of example only. Many other embodiments falling within the scope of the accompanying claims will be apparent to the skilled reader.

CLAIMS

1. A compostable sheet material comprising a compostable substrate layer, a first compostable and sealable layer on a first side of the substrate layer, and a
5 second compostable and sealable layer overlying said first sealable layer.
2. A compostable sheet material according to claim 1, wherein the material of the second sealable layer has a lower heat-sealing initiation temperature than the material of the first sealable layer.
- 10 3. A compostable sheet material according to any preceding claim, wherein the substrate comprises an oxygen barrier layer.
4. A compostable sheet material according to any preceding claim, wherein
15 the substrate comprises a layer of a printing substrate such as paper.
5. A compostable sheet material according to any preceding claim, wherein at least one of the first and second sealable layers comprise a polymer or copolymer of lactic acid.
- 20 6. A compostable sheet material according to any preceding claim, wherein the sheet material is at least about 90% composted within six months, as determined by the method of EN13432.
- 25 7. An environmentally friendly package comprising a compostable sheet material according to any of claims 1 to 6.
8. An environmentally friendly package according to claim 7, wherein the package comprises first and second regions of sealing between sheets of
30 compostable material according to the present invention, said first region having a relatively high heat sealing strength, and said second region having a relatively low sealing strength.

9. An environmentally friendly package according to any of claims 7 or 8, wherein the package is a beverage making capsule that contains a beverage making ingredient.
- 5 10. An environmentally friendly package according to claim 9, wherein the capsule further comprises a compostable filter sheet inside the capsule and bonded to an internal surface of the capsule.
11. A method of manufacture of an environmentally friendly package
10 comprising the step of providing a compostable sheet material according to any of claims 1 to 6, and sealing an area of said sheet material to form said package.
12. A method according to claim 11 comprising the steps of:
placing two webs of the compostable sheet material in face-to-face relation;
15 and
bonding the webs together around a margin to form a capsule body.
13. A method according to claim 11 or 12, wherein the step of sealing is carried out under a first set of conditions in a first region of said area and under a second
20 set of conditions different from said first set of conditions in a second region of said area, whereby the peel strength of the resulting seal is different in said first and second regions.
14. A method according to claim 11, 12 or 13 for the manufacture of an
25 environmentally friendly package according to any of claims 7 to 10.

ABSTRACT

COMPOSTABLE PACKAGING MATERIALS AND METHODS

- 5 A compostable sheet material comprising a compostable substrate layer, a first compostable and sealable layer on a first side of the substrate layer, and a second compostable and sealable layer overlying said first sealable layer. The use of more than one sealable layer allows greater control over sealing strength by varying the sealing conditions, for example heat and pressure. Also provided are
- 10 environmentally friendly packages comprising the inventive sheet material, and methods of making such packages.




Fig. 1.





Fig. 2.

*Fig. 3*

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.